

DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request" →

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 19, 2008

Mr. Loren Price
CATALINA CURTAIN COMPANY, INC.
P.O. Box 2589
Avalon, CA 90704

Reference: Laboratory Test Report
Lab Identification No. 7319
Invoice No. 19710 (Attached)

Dear Mr. Price:

One (1) fabric sample, identified as **STYLE 8864, AVALON**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". *Per your request, the sample was tested after seven (7) commercial laundering cycles at 160F (Tumble Dry)*. The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	23.91
2	0.0	21.75
3	0.0	25.70
4	0.0	26.30
5	0.0	18.11
6	5.0	22.21
7	0.0	20.41
8	0.0	24.39
9	0.0	18.00
10	8.0	23.69
AVG.	1.3	22.45


The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 6, 2008

Mr. Loren Price
CATALINA CURTAIN COMPANY, INC.
P.O. Box 2589
Avalon, CA 90704

Reference: Laboratory Test Report
Lab Identification No. 8143
Invoice No. 20506

Dear Mr. Price:

One (1) fabric sample, identified as "AVALON/8864", was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. *Per your request, the sample was tested after seven (7) commercial laundering cycles at 160F (Tumble Dry).* The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.9	3.1
2	0.0	0.0	4.8	4.7
3	0.0	0.0	3.7	4.5
4	0.0	0.0	4.4	4.1
5	0.0	0.0	4.0	4.0
Avg.	0.0	0.0		

The sample submitted **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment